



ARDEX EG 2

Epoxy Grout

Combines the chemical resistance of epoxy grouts, with application properties of cement based grouts

Ideal for use in swimming pools and other wet areas

For joint widths 1.5-10mm

Internal and external areas, walls and floors

Water based, low VOC, APEO free

Resistance to most common bathroom and kitchen stains

Available in a range of colors



本企业通过ISO9001:2000质量认证体系



ARDEX HONGKONG LTD.
Unit D, 16/F, CNT Tower,
No.338 Hennessy Road,
Wan Chai, Hong Kong
TEL: 852-25296325
FAX: 852-25298615

ARDEX (SHANGHAI) CO., LTD
3F, Building 13, No. 505,
South Zhongshan Rd.,
Shanghai, China
TEL: 86-21 61526722
FAX: 86-21 61526726
P.C.: 200010

ARDEX EG 2

Epoxy Grout

DESCRIPTION

ARDEX EG 2 Epoxy Grout combines the technical performance properties of an epoxy based grout with the ease of application associated with cement based grouts without requiring any special tools.

USE

ARDEX EG 2 is especially suitable for use in swimming pools, showers, bathrooms, shops, hydrotherapy and spa baths, sports centers and other specialized buildings where high standards of hygiene and cleanliness are required. ARDEX EG 2 is not recommended for use with high concentrations of foods such as commercial and industrial kitchens.

ARDEX EG 2 can be used for grouting different kinds of tiles, marble and glass mosaics with a joint width of 1.5-10mm, both internally and externally; see "notes"

MIXING

Completely dispense, then thoroughly mix the 2 liquid components (A+B) with a paddle or spatula by hand into the clean ARDEX EG 2 bucket for 1 minute until a uniform colour is achieved. Then slowly add Part C* (Powder) while continuing to mix until a homogenous mortar is produced. Use of a propeller type stirrer with a slow speed (<300rpm) drill is advantageous. ARDEX EG 2 mortar is then ready for immediate use and has a working time of approx. 30-45 minutes at 23°C. This is reduced at higher temperature and extended at lower temperatures.

*up to 10% of the powder can be left out for small joints and when used on the floor for easier workability and increased working time

Apply at temperatures above 5°C.

GROUTING

- Preparation of the joints:** Be sure all tiles are cleaned and joints prepared properly
- Application of grout:** ARDEX EG 2 is applied into the dry joint using a suitable grouting squeegee/float as per traditional cement based grouts. Excess grout should be removed as work proceeds.
- First Wash:** Approximately 20 minutes after the application of the grout, clean the surface of the tiles containing the slightly hardened grout in the joint
- Second Wash:** Approximately 60 minutes after the first wash, clean the tile surface using cold water and suitable sponge.

NOTES

- The mixing ratio of ARDEX EG 2 is accurately designed; do not mix ARDEX EG 2 with water.
- After ARDEX EG 2 is cured, any residues left on the surface of the tiles will be difficult to remove
- Certain types of tile may be prone to surface discoloration or scratching when using this grout, e.g. certain natural stones, absorbent tiles, textured tiles, and soft glazed ceramic tiles. Consult the tile manufacturer or distributor for advice or conduct a small scale test prior to installation.
- Tools should be cleaned before the mortar has hardened using a brush and water.
- When used externally ARDEX EG 2 may change color over time due to UV exposure. Please contact ARDEX Technical Services for advice of external applications.
- For steam rooms and submerged applications allow ARDEX EG2 to cure for 10 days at 23°C before turning on steam or filling with water
- Keep grout protected and free from dirt, dust, stains, etc during its curing period

SERVICE

- ARDEX EG 2 can accept light foot traffic after approx. 12 hours and heavy traffic after approx. 24 hours at 23°C (keep grout protected and free from dirt, dust, stains, etc during its curing period). The full cure time is 14 days and requires 7 days for full stain resistance at 23°C.**
- The cured grout can resist most common chemicals in residential and commercial circumstances.
- ARDEX EG 2 is able to accept the use of most common household detergents and is resistant to common household stains (i.e. coffee, tea, fruit juice, etc). All spills should be cleaned immediately.

** For details, please refer to the "Working Properties" table on the following page.

COVERAGE

You could estimate the consumption by the following formula.

$$\frac{(\text{length} + \text{breadth}) \times \text{width} \times \text{depth}}{\text{length} \times \text{breadth}} \times 1.7$$

the result is in kg/m²

Following are some common examples

Joint Width (mm)	Tile Dimension (mm)	Grout Consumption (kg/m ²)
3	200X100X6	0.46
2	150X150X5	0.25
2	100X100X5	0.35
2	50X50X5	0.68
5	50X50X5	1.70

We recommend considering at least 10% more consumption as the wastage due to application issues and tile surfaces.

PACKAGING

ARDEX EG 2 contains Parts A, B and C conveniently packaged in a mixing bucket. The normal colors are available in 2.5kg and 5kg while the glitter colors are available in 2kg.

STORAGE AND SHELF LIFE

Store in dry conditions. ARDEX EG 2 has a storage life of not less than 24 months in the original unopened container. Protect from freezing.

ARDEX EG 2

Epoxy Grout

TECHNICAL DATA

ARDEX EG 2 is compliant to ANSI A118.3 and tested according to JC/T1004-2006, EN 13888, ISO 13007 standards as an RG1

Reactive Resin Grout

JC/T1004-2006

Abrasion resistance	152 (loss in mm ³)
Flexural strength	>6MPa
Compressive strength	>23MPa
Shrinkage	1mm/m
Water absorption	0.05g/240min

Working Properties Table

	5°C	23°C	35°C
Working time	90mins	30-45mins	15-20mins
Light weight traffic	24hrs	12hrs	6hrs
Heavy weight traffic	48hrs	24hrs	12hrs
Resistance to stain	14days	7days	3days
Full cure	28days	14days	7days

PRECAUTIONS

In case of contact with the eyes, rinse immediately with plenty of water and seek medical advice and after contact with the skin wash immediately with plenty of soap and water (do not use solvents). Prolonged contact with the skin should be avoided, especially where the user has an allergic reaction to epoxide materials. Always wear gloves and eye/ face protection as necessary. Observe personal hygiene, particularly washing hands after work has been completed or at any interruption whilst work is in progress. Care should be taken when removing gloves to avoid contaminating the insides. In case of accidents seek medical advice.

The information supplied in our literature or given by our employees is based upon extensive experience and, together with that supplied by our agents or distributors, is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products; however, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.